

QuickSeam FormFlash

1. Description

FormFlash is a self-curing rubber strip, adaptable to irregular shapes and designed to flash system details (inside and outside corners, pipes, reinforcement patches...) in accordance with Firestone specifications. The FormFlash layer is factory laminated to QuickSeam Tape.

The product is available in the following format:

- QuickSeam FormFlash 9" : a 229 mm wide strip
- QuickSeam FormFlash 12" : a 305 mm wide strip
- QuickSeam FormFlash 18" : a 457 mm wide strip



2. Preparation

The PondGard™ membrane surfaces must be prepared with QuickPrime Plus, using a QuickScrubber tool. Use of other products is not allowed. Restore the FormFlash product to room temperature prior to use if exposed to temperatures below 15°C for prolonged periods.

3. Application

On cloudy days with ambient temperature below 15°C, the use of a heat gun is recommended to warm the QuickSeam FormFlash and ensure good formability.

On sunny days, pre-heating of the product is usually not necessary. On sunny days less than 20°C, place QuickSeam FormFlash (prior to application) with flashing side up to allow QuickSeam FormFlash to warm to ensure good formability. On sunny days greater than 20°C, place QuickSeam FormFlash (prior to application) with release paper side up to prevent QuickSeam FormFlash from getting too hot.

QuickSeam FormFlash is to be applied as per the Firestone specifications and details.

4. Coverage

In accordance with length of detail. Pieces must overlap a minimum of 75 mm and extend a minimum of 75 mm beyond critical points.

5. Characteristics

The Firestone QuickSeam FormFlash is a rubber material with the following properties:

Technical	EPDM Flashing	QuickSeam Tape
• Base	EPDM	rubber polymers
• Color	black	black
• Solvents	none	none
• Solids (%)	100	100
• State	uncured	cured
• Thickness	1.6 mm	0.6 mm

6. Precautions

Take care when moving, transporting or handling to avoid sources of punctures and physical damage. Isolate waste products, such as petroleum products, greases, oils (mineral and vegetable) and animal fats from Firestone QuickSeam FormFlash. As long as product is not fully cured, QuickSeam FormFlash has limited chemical and root resistance.

Store in original unopened carton at temperatures between 15°C and 25°C. Keep the material out of direct sunlight until ready for application.

Shelf life is expected to be 12 months, when stored in above-mentioned conditions. Verify production date on each roll. Shelf life will be reduced if exposed to higher temperatures.